

Table 2. Cyclic stress-strain curve properties.

k' [MPa]	n'	Stress relieved
1314	0.043	
k' [MPa]	n'	HIPed
1176	0.036	
k*[MPa]	n*	Stress relieved
2275	0.155	
k* [MPa]	n*	HIPed
1695	0.111	