

*Table 1. Estimates of the specific surface area of graphene-based scaffolds relative to SA scaffold*

Sample	Mean pore size ( $\mu\text{m}$ )	Normalized Specific Surface Area
SA	162.5	1
GOSA0.5	147.4	0.907
GOSA1	142.5	0.876
RGOSA0.5	116.0	0.713
RGOSA1	114.7	0.705